TECASAFE®PLUS

ENGINEERED FOR THE FIRE SERVICE

Tecasafe®Plus Swiss Pique

COLOR AND CONFIDENCE

Tecasafe® Plus Stationwear stands up to repeated laundering and resists fading thanks to Truecolor® technology.

PROTECTION THAT LASTS FOREVER

Inherent FR protection from a name you know and trust.

DRY, COOL, AND COMFORTABLE

Integrated wicking Coolderm™ technology offers enhanced moisture management to promote body temperature regulation and breathability.

TENCATE protectivefabrics | *made for life*

TECASAFE®PLUS

TECHNICAL DATA*		TECASAFE®PLUS SP TRUECOLOR®
Nominal Weight		6.7 osy (227 gsm)
Construction		Knit
Color		Navy, Heather Gray, Gray, Black
Fiber Content		Modacrylic, Lyocell, Aramid
Certification(s)		NFPA 1975
Thermal Performance		
Flame Resistance	Before laundering and after 100 laundering cycles	Compliant
Thermal Shrinkage	Before and after 3 laundering cycles	< 10 %
Physical Performance		
Burst Strength – Ball Method		105 lbf (460 N)
Burst Strength – Mullen Method		100 psi (675 kPa)
Dimensional Stability AATCC 135		< 5.0 %
Fabric Stretch and Recovery warp x fill	Fabric Stretch	32 % x 20 %
	Fabric Recovery	90 % x 94 %
Comfort		
Air Permeability		170 $ft^3/ft^2/min$

* All values subject to final certification and specification. Tested on specific colors. Appearance is dependent on shade of fabric.

AVAILABLE COLORS

Navy | Heather Gray | Gray | Black

OPTIONAL COLORS

TenCate Protective Fabrics, the world's textile dyeing expert, can produce almost every color with a minimum quantity of 3000 yards. Smaller quantities can be ordered, subject to a surcharge. For more information, please contact TenCate Protective Fabrics.

MADE IN USA WITH GLOBAL COMPONENTS

OEKO TEX® STANDARD 100 1604026 Centexbel

TenCate Protective Fabrics is certified according: ISO 9001 ISO 14001 BUREAU VERITAS Certification

Corporate Social Responsibility

All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.