
| TECAPRO®



TECAPRO® SATIN LINE BG 9045 – 450 g/m²

EXTREME SOFTNESS AND FLEXIBILITY

Feels soft and supple thanks to the 4/1 satin construction, high amount of cotton and Comfort-Control finish.

OUTSTANDING METAL AND SPARK PROTECTION

Due to a smooth surface, molten metal splashes and sparks run right off.

UNBEATABLE VALUE FOR MONEY

Retains its strength even after extensive industrial laundering - minimizing cost of ownership.





TECHNICAL DATA*	TECAPRO® SATIN LINE	TEST METHOD
Quality	BG 9045	
Width	153 cm (+2/-1 cm)	ISO 3801: 1978
Weight	450 g/m² (± 5%)	ISO 3932: 1980
Composition	co/pes/Static-Control™ 79/20/1%	
Construction	4/1 Satin	
Available finishes	Standard: Durable flame-retardant finish with Comfort-Control and Hydro-Tec	
Physical performance		
Tensile strength	1950 N x 900 N (±10%)	ISO 13934-1: 1999
Care labelling		
Domestic laundering	₩ № @ P	To keep these fabrics looking at their best, contact TenCate for laundering,
Industrial laundering	75 °C	care and maintenance advice.
Protection	Multi-risk	
PPE requirements*		

CERTIFICATION*		
©	Industrial flame & heat hazards	EN ISO 11612 A1,A2,B1,C1,E3,F1: 2015 (A1 + A2= 50 x ISO 15797 - 75 °C)
	Electric Arc	EN IEC 61482-1-2, class 1: 2015 HRC/Category 2 ($8 \le ATPV \le 25 \text{ cal/cm}^2$)
<u> </u>	Welding	EN ISO 11611, class 2: 2015
<u> </u>	Anti-static for explosion risk	EN 1149-5: 2018, EN 1149-3: 2004
	Liquid chemicals**	EN 13034: 2005 + A1: 2009
	General requirements***	EN ISO 13688: 2013

- Copyright symbols: NEN, Delft (Netherlands)
- ** Hydro-Tec finish only

 *** Tested on specific colours

COLOURS							
River	Navy	Vulcano	Charcoal	Steelorange	Papaya	Black	
60662	63805	66935	65576	65596	61070	60475	

Ten Cate Protect B.V. is certified according:





Member of the E.T.S.A.

All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.